


ZELUX® GS

Gamma Stabilized

Zelux® is a Registered Trademark of Westlake Plastics Co.

Medical grade Zelux GS polycarbonate is produced from resin formulated to meet the stringent performance characteristics and requirements of the healthcare industry. Suitable for gamma, E Beam, EtO gas and limited autoclaving sterilization, the resin utilizes proprietary color enhancement technology to reduce color shift caused by gamma radiation.




The following physical property information is based on typical values of the base gamma stabilized polycarbonate resin.

Property	Units	Test Standard	Result
Mechanical			
Flexural Modulus	psi	ASTM D790	339,000
Flexural Strength @yield	psi	ASTM D790	14,100
Izod Impact Strength			
Notched	ft·lbs/in	ASTM D256	17.0
Un-Notched	ft·lbs/in	ASTM D256	60.0
Tensile Elongation @break	%	ASTM D638	135.0
Tensile Strength			
@break	psi	ASTM D638	9,900
@yield	psi	ASTM D638	8,900
Thermal			
Coefficient of Thermal Expansion	—	ASTM E831	3.44x10 ⁻⁵
Heat Deflection Temperature			
@66 psi (.250")	°F	ASTM D648	280
@264 psi (.250")	°F	ASTM D648	270
Other			
Specific Gravity	—	ASTM D792	1.20

Applications Include:

- Surgical equipment
- Instrument components
- Housings and covers

Manufacturing Capabilities:



Colors:

Transparent w/ Blue Tint

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.



Phone : 1.610.459.1000
 Phone : 1.800.000.1700
 Fax : 610.459.1084
 490 West Lenni road
 Lenni, PA 19052
 U.S.A
 Email : info@westlakeplastics.com



EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.